

ECT Mfg.
 11 Black Forest Rd.
 Hamilton, NJ 08691
 Tel. (888) 240-4328

AQUA-SLEEVE®
 PERFORMANCE DATA GUIDE

ECT Mfg.
 ectmfg.com
 sales@ectmfg.com
 (609) 631-8939

			AQUA-SLEEVE® PRODUCT NUMBERS				
Characteristics	Test Method	UOM	WM-0101	WM-0201	WM-0401	WM-0601	WM-0801
Nominal Size		inches(mm)	1" (25mm)	2" (50mm)	4" (100mm)	6" (150mm)	8" (200mm) to 12" (300mm)
Roll Length		ft (m)	100ft (30m)				
Apparent Opening Size (AOS)	ASTM D4751	mm	<0.075	0.112	0.212	0.150	0.150
US Standard Sieve Size			200	120	70	100	100
Water Flow Rate	ASTM D4491 @ 2" constant head	US gpm/ft ²	70	80	140	112	155
Permeability	ASTM D4491	cm / sec	2.5	1.2	3.1	1.3	3.7
Fabric Composition			84%Polyester 16% Lycra	100% Polyester			
Specific Gravity			1.3				
Melt Temperature			450° F / 230°C				

NOTES:

- 1) Values reported are based on independent laboratory evaluation and are considered to be true and accurate.
- 2) The manufacturer certifies that all values provided are indicative of the fabric's properties at the time of manufacture and shipment to the original purchaser only. This certification is not transferable. Any required certifications of compliance to a specific characteristic are the responsibility of the final seller or user of the fabric.

Effective: December 2020